

Припой экологический бессвинцовый  
SAC0307(SnAg0,3Cu0,7)

Pb*	Cd	Sb	Bi	Fe	Zn	Al	As	other
0,10%	0,002%	0,05%	0,05%	0,02%	0,001%	0,001%	0,01%	0,08%

\* - real contents of Pb max 0,06% (600 ppm)



БелТерраТранс-официальный торговый партнер  
Synel Unipress в России и Беларуси.

### 3. Physical characteristics

3.1 Melting point:	216 - 227 °C
3.2 Density:	7,44 g/cm <sup>3</sup>
3.3 Calority:	0,17 J/kg/°C
3.4 Wetting speed:	0,75s
3.5 Tensile strength:	29,5 N/mm <sup>2</sup>

### 4. Physical characteristics

4.1 Assortment:	wires from 0,25 mm to 5,00 mm diameters
4.2 Bars / rods dimensions:	- extruded bars 7 x 7 x 350, 7 x 21 x 350, 10 x 40 x 350 mm - triangle cast bars 12 x 12 x 400 mm - bars 10 mm x 40 mm x 1kg - bars 20 mm x 40 mm x 550 mm

### 5. Packaging

- 5.1 Spooled wire 250 g, 500 g, 1 kg, or by arrangement.
- 5.2 Cartooned by 10 kg.  
Bars cartooned: - extruded bars by 25 kg, cast bars by 20 kg.
- 5.3 Spools and cartoons marked with solder type, diameter and batch number.

The product meets the requirements of the RoHS Directive 2002/95/EC and requirements of other regulations concerning the use of harmful substances (such as Dz.U. Nr 229 dated October 21, 2004 Poz. 2310)



Телефон в Москве +7 (499) 500 94 02;  
Телефон в Минске +375 (29) 707 79 46;

E-mail: [belterratrans@gmail.com](mailto:belterratrans@gmail.com)  
Веб-сайт: <http://belterratrans.com/>

