


Припой свинцовый в прутах S-Pb78Sn20Sb2 (LC20A1(2))



09 June 2010



БелТерраТранс-официальный торговый партнер
Cynel Unipress в России и Беларуси.

1. General characteristics

S-Pb78Sn20Sb2 solder manufactured in the first melt of tin, lead and antimony according to PN EN 29453:2000 standard in continuous casting process in air-free environment; afterwards extruded, in order to eliminate oxide occurrence..

2. Chemical characteristics

- 2.1 Tin contents: 19,5% to 20,5%
2.2 Antimony contents: 0,5% to 3,0%
2.3 Lead contents: rest
2.4 Tin, lead and antimony of first smelting purity: 99,90%
2.5 Max. impurities:

Cu	Cd	Bi	Fe	Zn	Al	As	other
0,08%	0,005%	0,25%	0,02%	0,001%	0,001%	0,03%	0,08%

3. Physical characteristics

- 3.1 Melting point: 185°C to 270°C
3.2 Density: 10,20 g/cm³
3.3 Assortment:
- wires with or without flux from 0.7 mm to 5.00 mm diameters
- extruded bars 7 x 7 x 350 mm
3.4 Working temperature: 340°C to 450°C

4. Packaging

- 4.1 Spooled wire 1 kg and 10 kg, bars cartooned by 25 kg.
4.2 Products marked with solder type, cartons marked by kind of solder, flux type, diameter and batch number.